SPECIFICATION CONTROL DRAWING

CHEMINAX

75 OHM, AWG 22, 19 STRANDS OF AWG 34, TWINAXIAL CABLE

12-7-12 Date Revision Α

75 ± 7 ohms, Method C at 1 MHz

15.5 ohms/1000 ft. (nominal)

30.0 pF/ft. (nominal)

66% (nominal)

7522B0331

THIS SPECIFICATION SHEET FORMS A PART OF THE LATEST ISSUE OF RAYCHEM SPECIFICATION 1200

CHARACTERISTIC IMPEDANCE

VELOCITY OF PROPAGATION

MUTUAL CAPACITANCE

CONSTRUCTION DETAILS

ELECTRICAL CHARACTERISTICS

ADDITIONAL REQUIREMENTS

DIMENSIONS ARE NOMINAL VALUES IN INCHES UNLESS OTHERWISE DESIGNATED

CONDUCTORS AWG 22, 19 Strands of .0315 AWG 34, Tin-Coated Copper **DIELECTRICS** .060 Rayolin F ±.003 Colors - Tan/White **DRAINWIRE**

ELECTRICAL

AWG 22, 19 Strands of

AWG 34, Tin-Coated

Aluminum Polyester

Copper

WRAP

JACKET

Outer jacket color will be black (designated by a "-0" appended

Designate outer jacket color with a dash number in accordance with MIL-STD-681. Other codes and suffixes may be added to the part number, as necessary, to capture any additional

to the part number, e.g. 7522B0331-0) unless otherwise

requirements imposed by the purchase order.

Thermorad S

CONDUCTOR RESISTANCE (prior to cabling)

> INSULATION RESISTANCE 10,000 megohms (minimum)

> > for 1000 ft.

JACKET FLAWS

1.0 kV (rms) SPARK TEST IMPULSE TEST 6.0 kV (peak)

VOLTAGE WITHSTAND (DIELECTRIC) 1000 volts (rms) (minimum)

ENVIRONMENTAL

FLAMMABILITY Method C 225°C **HEAT SHOCK**

LOW TEMPERATURE-COLD BEND -55°C/4.25 inch mandrel **VOLTAGE WITHSTAND** 1000 volts (rms), 1 minute

(Post Environmental)

PHYSICAL

INSULATION (DIELECTRIC)

(Prior to Cabling)

ELONGATION 200% (minimum) TENSILE STRENGTH 1800 lbf/in2 (minimum)

ELONGATION 200% (minimum) 2000 lbf/in2 (minimum) TENSILE STRENGTH JACKET THICKNESS .013 inch (nominal)

WRAP .002 inch thick (nominal) 25% minimum overlap

Aluminum side facing out

WEIGHT 14.4 lbs/1000 ft. (nominal)

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice. Tyco Electronics Corporation also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

Page 1 of 1

specified.

.128

.154

Rayolin, Thermorad, Cheminax, Raychem, TE Connectivity, TE connectivity (logo) and TE (logo) are trademarks.

