

SPECIFICATION CONTROL DRAWING

55/LF0314

| | | |
|--|-----------------|---------------|
| TITLE WIRE, RADIATION-CROSSLINKED, MODIFIED ETFE-INSULATED, ULTRA LOW FLUORIDE, ULTRA LIGHTWEIGHT, OUTER SPACE, 600 VOLT | Date 1-21-08 | Revision B |
|--|-----------------|---------------|

This specification sheet forms a part of the latest issue of Raychem Specification 55/.




TABLE I. CONSTRUCTION DETAILS

| PART NUMBER 1/ | WIRE SIZE (AWG) | CONDUCTOR STRANDING (number x AWG) | DIAMETER OF STRANDED CONDUCTOR (in.) | | FINISHED WIRE | | |
|-------------------|--------------------|---------------------------------------|---|---------|---|-------------------|----------------------------------|
| | | | MINIMUM | MAXIMUM | MAXIMUM RESISTANCE AT 20°C (ohms/1000 ft) | DIAMETER (in.) | MAXIMUM WEIGHT (lbs/1000 ft.) |
| | | | | | | | |
| 55/LF0314-30-* | 30 | 7 x 38 | .0110 | .0120 | 117. | .0195 ± .0015 | .56 |
| 55/LF0314-28-* | 28 | 7 x 36 | .0140 | .0150 | 74.4 | .0225 ± .0015 | .81 |
| 55/LF0314-26-* | 26 | 19 x 38 | .0175 | .0191 | 44.8 | .0274 ± .0017 | 1.23 |
| 55/LF0314-24-* | 24 | 19 x 36 | .0225 | .0241 | 28.4 | .0322 ± .0017 | 1.79 |
| 55/LF0314-22-* | 22 | 19 x 34 | .0285 | .0301 | 17.5 | .0390 ± .0017 | 2.70 |
| 55/LF0314-20-* | 20 | 19 x 32 | .0365 | .0385 | 10.7 | .0495 ± .0017 | 4.27 |

TABLE II. PERFORMANCE DETAILS

| PART NUMBER 1/ | BEND TESTING | |
|-------------------|-----------------------------------|------------------------|
| | MANDREL DIAMETER (inch) (± 3%) | WEIGHT (lb) (± 3%) |
| | CROSSLINK VERIFICATION | CROSSLINK VERIFICATION |
| | 55/LF0314-30-* | .250 |
| 55/LF0314-28-* | .250 | .063 |
| 55/LF0314-26-* | .375 | .063 |
| 55/LF0314-24-* | .375 | .125 |
| 55/LF0314-22-* | .500 | .188 |
| 55/LF0314-20-* | .500 | .250 |

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice. Tyco Electronics also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

1/ COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681. OTHER CODES AND SUFFIXES MAY BE ADDED TO THE PART NUMBER. AS NECESSARY, TO CAPTURE ANY ADDITIONAL REQUIREMENTS IMPOSED BY THE PURCHASE ORDER.

| | | | |
|-------------|---|---|---|
| Page 1 of 2 | The TE logo, Tyco Electronics and Raychem are trademarks. |  | Raychem Wire & Cable 501 Oakside Avenue Redwood City, CA 94063-3800 Phone: 1-800-227-8816 Fax: 1-650-361-6297 |
| | DIMENSIONS ARE IN INCHES, AND UNLESS OTHERWISE DESIGNATED ARE NOMINAL | | |
| | THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID. | | |

WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 200°C

Maximum continuous conductor temperature

VOLTAGE RATING: 600 volts (rms) at sea level

CROSSLINK VERIFICATION: 300 ± 3°C for 1 hour

COLOR: White preferred

CONCENTRICITY: 80% (minimum)

FLUORIDE EXTRACTION: 70 ± 2° C for 168 hours, 20 ppm (maximum)

IDENTIFICATION AND COLOR STRIPING DURABILITY:

125 cycles (250 strokes) (minimum), 500 g weight

INSULATION ELONGATION: 50% (minimum)

INSULATION FLAWS:

Spark Test, 1.5 kV (rms), (30 - 24 AWG)

3.0 kV (rms), (22 AWG & larger)

Impulse Dielectric Test, 6.0 kV (peak)

INSULATION THICKNESS: 0.004 in. (nominal)

RADIATION RESISTANCE: 500 megarads

SHRINKAGE: 230 ± 3°C for 1 hour, 0.125 in. (maximum) in 12 in.

VACUUM STABILITY:

Total Mass Loss (TML), 1.00% (maximum)

Volatile Condensable Material, 0.10% (maximum)

VOLTAGE WITHSTAND TEST (Post Environmental): 1500 volts (rms), 60 Hz, 5 minutes

PART NUMBER:

The "*" in the part numbers on page 1 shall be replaced by a color code designator.

1/ Example: AWG 22, white: 55/LF0314-22-9

AWG 22, white with black stripe: 55/LF0314-22-90

1/ See footer section on page 1